


Câbles forestiers -SWAGED- câbles martelés
Swaged ropes for forestry
Forstseile



druforest 6/26

Nominal diameter Nenn-Durchmesser	Approximated weight of the rope Längengewicht (ca.)	Minimum breaking force Mindest-Bruchkraft
		1960 N/mm ²
mm	kg/100m	kN
8,0	36,1	67,4
9,0	44,1	82,3
10,0	52,9	98,8
11,0	62,5	117
12,0	72,9	136
13,0	84,1	157
14,0	96,1	180
15,0	108,9	203
16,0	122,5	229